

# Hike TRANSMISIONES HD GL-5



**90, 140, 80W90, 85W90, 85W140**

## Description

Hike TRANSMISIONES HD GL-5 series of lubricants are high performance heavy duty gear oils, formulated from high quality base oils and an advanced additive system. These lubricants are designed for automotive heavy-duty transmissions, axles and final drives. Moreover these oils are specially engineered for heavy-duty axles and final drives where extreme pressures and shock loadings are expected.

## Application

Hike TRANSMISIONES HD GL-5 series are suitable for use in all Passenger cars, On-highway light and heavy dutytrucks, and commercial vehicles.

- Suitable for Heavy duty manual transmissions, axles and final drives requiring API GL-5 levelperformance.
- Applications like Off-highway industries including: construction, mining, quarrying, and agriculture.
- Other heavy-duty industrial and automotive applications, involving hypoid gears operating under conditions where high speed/shock load, high speed/low torque, and/or low speed/high torque exists.

## Features & Benefits

- Exceptional thermal & oxidation stability protects against deposit formation and oil thickening, thus maintains the life and performance of lubricant and transmission.
- Outstanding anti-wear properties and excellent film strength provides exceptional equipment protection, that not only results in fewer breakdowns but also helps improve transmission efficiency.
- Excellent rust and corrosion protection for longer component life.
- Compatibility with seals and gaskets, leads to minimize oil leakage and reduced contamination.

## Specifications

**Hike TRASMISIONES HD GL-5 meets or exceeds following International and Builder specifications:**

- API GL-5
- MIL-L-2105D (U.S Military Specification)

## Typical Characteristics\*

Hike TRASMISIONES HD GL-5	Test Method	Units	90	140	80W90	85W90	85W140
Density @ 15 °C	ASTM D 4052	gm/cc	0.890	0.910	0.888	0.890	0.908
Viscosity @ 40 °C	ASTM D 445	cSt	145	447	146	190	356
Viscosity @ 100 °C	ASTM D 445	cSt	14.3	30.0	14.7	17.4	25.6
Viscosity Index	ASTM D 2270	-	96	95	100	97	95
Pour Point	ASTM D 97	°C	-12	-9	-24	-24	-15
Flash Point (COC)	ASTM D 92	°C	240	260	230	236	248
Copper Strip Corrosion	ASTM D 130	-	1B	1B	1B	1B	1B
Foam Seq I,II,III	ASTM D 892	ml/ml	10/0	20/0	10/0	10/0	20/0
Phosphorus	ASTM D 4951	%wt	0.055	0.055	0.055	0.055	0.055

\* The above figures are typical of blends with normal production tolerance and do not constitute a specification.

For further information, please contact; [Info@hikelube.com](mailto:Info@hikelube.com)

[www.hikelube.com](http://www.hikelube.com)

Powered by HIKE Company Madrid –Spain

Revision 3: December,2021

